

# **RIVERWOOD**

## colors



#### RIVERWOOD / CHERRY



#### RIVERWOOD / GUNSTOCK



#### RIVERWOOD / WALNUT

#### sizes:

6"x36"



1099481





#### sizes:

6"x36"



1099532





#### sizes:

6"x36"



1099480





#### TECHNICAL SPECIFICATIONS

|            | SPECS                         | TEST METHOD    | INDUSTRY STANDARD  | MILE®STONE VALUES                   |  |
|------------|-------------------------------|----------------|--|-------------------------------------|--|
|            | WATER ABSORPTION              | ASTM<br>C373   | ≤0.5%  | ≤0.4%                               |  |
| · <b>\</b> | CHEMICAL RESISTANCE           | ASTM<br>C650   | A tile sample is placed in continuous contact with<br>a variety of chemicals for 24 hours.<br>No sample must show visible defects.   | NOT AFFECTED                        |  |
| *          | D.C.O.F. AcuTest <sup>⊚</sup> | ANSI<br>A326.3 | ≥0.42% WET   | ≥0.42% WET                          |  |
| ×          | STAIN RESISTANCE              | ASTM<br>C1378  | Surfaces are exposed to staining agents for 24 hours<br>followed by four cleaning procedures.<br>Results are recorded post cleaning. | NOT AFFECTED                        |  |
| ڡ۠         | BREAKING STRENGTH             | ASTM<br>C648   | ≥250 lb/ft2  | 8mm ≥300 lb/ft2<br>10mm ≥400 lb/ft2 |  |
| ₩          | RESISTANCE TO<br>FREEZE       | ASTM<br>C1026  | A tile sample is subjected to repeated<br>processes of freezing and thawing.<br>Sample must show no visible defects.                 | RESISTANT                           |  |
|            | WARPAGE EDGE ASTM             | ASTM<br>C485   | Warpage ± 0.4%<br>or ± 0.05 in   | ≥± 0.4%                             |  |
|            | WARPAGE DIAGONAL              | ASTM<br>C485   | Warpage ± 0.4%<br>or ± 0.07 in   | ≥± 0.4%                             |  |
|            | WARPAGE EDGE ASTM             | ASTM<br>C485   | Warpage ± 0.5%<br>or ± 0.07 in   | ≥± 0.5%                             |  |
|            | WARPAGE DIAGONAL              | ASTM<br>C485   | Warpage ± 0.5%<br>or ± 0.07 in   | ≥± 0.5%                             |  |
| 4          | WEDGING                       | ASTM<br>C502   | ± 0.25% or ± 0.03 in   | ≥± 0.25%                            |  |
| <u>.</u>   | THICKNESS                     | ASTM<br>C499   | Range: ± 0.04 in   | ≤0.04 in                            |  |

• Due to the inherent nature of fired porcelain tile, it is important to note that the coefficent of friction may vary within and between product runs.

### packaging

| SIZES          | METRIC<br>(CM) | THICKNESS<br>(MM) | PIECES PER<br>BOX | UOM PER<br>BOX | WEIGHT PER<br>BOX | BOXES PER<br>PALLET | UOM PER<br>PALLET | WEIGHT PER<br>PALLET* |
|----------------|----------------|-------------------|-------------------|----------------|-------------------|---------------------|-------------------|-----------------------|
| FIELD TILES    |                |                   |                   |                |                   |                     |                   |                       |
| 6"x36" PRESSED | 15x90          | 10                | 8                 | 12 SF          | 54.4              | 48                  | 576 SF            | 2,534                 |

\* WEIGHT PER PALLET DOES NOT INCLUDE PALLET WEIGHT ITSELF.

